

# Technical Data Sheet

Enjoy HWR

Class 33 according to DIN EN 13329:2024-03




**CLASSEN**

Version: 05/2025

**Profile:** **megaloc**  
aqua protect

**Core board:** Classenboard HDF  
**Dimensions:** 1285 x 192 x 8 mm  
**Quantity / Weight per box (PU):** 9 pieces = 2.220 m<sup>2</sup> / approx. 17 kg  
**Quantity / Weight per pallet:** 44 PU = 97,68 m<sup>2</sup> / approx. 760 kg

Characteristics	Test Method	Requirements
<b>General Requirements</b>		
Geometrical characteristics	EN 17539	Length: ± 0.5 mm Width: ± 0.1 mm
Thickness	EN 17539	± 0,5 mm
Squareness	EN 17539	max. ≤ 0.20 mm
Straightness	EN 17539	max. ≤ 0.30 mm/m
Flatness of the elements	EN 17539	Width: concave ≤ 0.15%, convex ≤ 0.20 % Length: concave ≤ 0.50 %, convex ≤ 1.00 %
Openings	EN 17539	∅ ≤ 0.15 mm max. ≤ 0.20 mm
Height difference	EN 17539	∅ ≤ 0.10 mm max. ≤ 0.15 mm
Light fastness	 EN ISO 489-2:2013	Grey scale level ≥ 4
Residual indentation	 EN ISO 24343-1	≤ 0.05 mm
<b>Classification Requirements</b>		
Wear resistance	 ISO 24338 Method A	≥ 6,000 cycles (AC5)
Impact resistance	 EN 17368 DIN EN 13329:2024-03 Annexe C	Small-diameter ball ≥ 70 mm Large-diameter ball ≥ 750 mm
Resistance to staining	 EN 438-2	5 (group 1 and 2), 4 (group 3)
Movement of a furniture leg	 EN ISO 16581	No visible damage with type 0
Castor chair resistance	 EN ISO 4918	No visible damage with type W after 20,000 cycles
Thickness swelling	 ISO 24336	≤ 15 %
Locking strength	 ISO 24334	f <sub>10,2</sub> ≥ 1.0 kN/m f <sub>s0,2</sub> ≥ 2.0 kN/m
Surface soundness	DIN EN 13329:2024-03 Annexe B	≥ 1.25 N/mm <sup>2</sup>
<b>Essential Characteristics</b>		
Reaction to fire*	 EN 13501-1	C <sub>fl</sub> - s1
Slip resistance*	 EN 13893	DS
Electrostatic behavior*	 EN 1815	≤ 2 kV
Formaldehyde*	 EN 16516	E1
Formaldehyde-Emissions	ASTM D6007	US EPA TSCA Title VI / CARB P 2
Thermal conductivity*	 EN 12667	≥ 0.075 W/mK
Thermal resistance*	 EN 12667	R ≤ 0,058 (m <sup>2</sup> K)/W
<b>Additional requirements</b>		
Topical moisture resistance-surface swell	ISO 4760	- Qualitative recovery swell rating final average < 3 - Recovery swell final average ≤ 0,3 mm swelling
Topical moisture resistance-water tightness of the joints	ISO 4760	No water leakage through the joints after 168 h water exposure
VOC Emissions	  <a href="http://www.blauer-engel.de/uz176">www.blauer-engel.de/uz176</a> - low emissions and pollutants - wood from sustainable forestry - no adverse impact on health in the living environment	  <b>A+</b>
Sustainability		

Disposal: Private: with normal household waste / bulky waste possible | Commercial: European Waste Catalog: Waste code 17 02 03

We guarantee consistency of our decor colours under artificial light of type D50 (CIE D50, ANSI PH 2.30, ISO 3664) and D65 (CIE D65).

\* basic attributes concerning health, safety and energy saving acc. to **CE** EN14041

Our technical data sheets are constantly updated and adapted to the state of the art.

CLASSEN Holz Kontor GmbH, Werner-von-Siemens-Str. 18-20, DE-56759 Kaisersesch

This edition replaces all previous versions and is valid at the time of writing.

This document is valid without signature.